

PROTECTAMESH™ BRS13
Rockshield

Product Data Sheet

Composition:

High density polyethylene, diamond mesh with carbon black and blowing agent.

Mesh Mechanical properties

(Mean values)

Tensile Strength (MD)	EN ISO 10319	kN/m	4.6
Elongation @ break (MD)	EN ISO 10319	%	45
Compressive strength	ASTM 1621	Kpa	900
Impact resistance	ASTM G14	Kgf-m	2.19

Physical properties (Typical values)

Thickness	mm	3.5
Mesh Count		22 in 20cm
Weight per m ²	g	500

Roll dimensions

Roll Width	m	1.84
Roll length	m	30.5

As part of its continual improvement process Fiberweb Geosynthetics Ltd reserve the right to change the properties listed on this data sheet without prior notice.

TM indicates a trade mark of Fiberweb plc or a Fiberweb Group company, many of which are registered in a number of countries around the world.